

**PRODUCT: CYCLE RIKSHAW TYRES**

<u>Ingredients</u>	<u>Quantity (PHR)</u>
R M A	60
P B R	20
Reclaim	40
China Clay	50
H A F Carbon	15
<u>HARITSIL 400 B</u>	<u>20</u>
Zinc Oxide	5
T D Q	1.0
4020	0.5
Process Oil	6-10
<u>Stearic</u>	1.5
<u>Sulphur</u>	2.5
Wax	1.0
C B S	1.1
T M T	0.2

Cure Temp. 150 C

Cure Time 3'